


Somos[®] 9120[™]

Stereolithography

A translucent stereolithography material for when you need to see the inner workings of the part you're creating.

Somos[®] 9120 is a transparent stereolithography resin that is easy to use and fast to build.
This stereolithography resin produces translucent, accurate parts that are semiflexible.
Parts produced with Somos[®] 9120 exhibit excellent water and temperature resistance and mimic polypropylene.

Somos® 9120 is ideal for applications such as fluid flow analysis, electrical casings and automotive parts. As this material is semi-flexible, it can also be used for snap-fit functional testing.



Key Benefits

- Highly transparent
- Semi-flexible
- Easy to use and finish

Ideal Applications

- Automotive parts
- Electrical casings
- Fluid flow analysis

LIQUID PROPERTIES		OPTICAL PROPERTIES		
Appearance	Clear	E _c	10.9 mJ/cm ²	[critical exposure]
Viscosity	~450 cps @ 30°C	D _P	5.6 mils	[slope of cue-depth vs. In (E) curve]
Density	~1.13 g/cm ³ @ 25°C	E ₁₀	65 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]



MECHANICAL PROPERTIES		UV POSTCURE		
ASTM Method	Property Description	Metric	Imperial	
D638M	Tensile Modulus	1,350 MPa	7.3 ksi	
D638M	Tensile Strength	31 MPa	4.5 ksi	
D638M	Elongation at Yield	20%		
D790M	Flexural Strength	45 MPa	6.5 ksi	
D2240	Flexural Modulus	1,380 MPa	200 ksi	
D256A	Izod Impact (Notched)	51 J/m	0.95 ft-lb/in	
D2240	Hardness (Shore D)	81		

These values may vary and depend on individual machine processing and post-curing practices.

USA - Headquarters

7665 Commerce Way Eden Prairie, MN 55344, USA +1 952 937 3000

ISRAEL - Headquarters

1 Holtzman St., Science Park PO Box 2496 Rehovot 76124, Israel +972 74 745 4000

stratasys.com

ISO 9001:2015 Certified

EMEA

Airport Boulevard B 120 77836 Rheinmünster, Germany +49 7229 7772 0

ASIA PACIFIC

7th Floor, C-BONS International Center 108 Wai Yip Street Kwun Tong Kowloon Hong Kong, China + 852 3944 8888



GET IN TOUCH. www.stratasys.com/contact-us/locations

© 2022 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Somos and 9120 are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. MDS_SL_Somos-9120_A4_0123a